


BLACKOUT 100%

SATINÉ 21154



INTELLIGENT FABRICS FOR SOLAR PROTECTION



SATINÉ 21154

THE BLACKOUT FABRIC WHICH MATCHES SATINÉ 5500

FABRIC FOR THE BALANCE OF THE FACADE

100% **BLACKOUT** AND THERMAL COMFORT

210 CM LARGE WIDTH

- The blackout screen-looking fabric for **EXTERNAL AND INTERNAL** TOTAL BLACKOUT ROLLER BLIND SYSTEMS (with retentive buttons/ studs, deep side channels...)
- Perfect match with side channels systems such as **ZIP**
- 100% OF LIGHT AND UV RAYS BLOCKED at 100.000 Lux
- THERMAL COMFORT: rejects up to 99% OF SOLAR ENERGY (gtot = 0.01 / glazing g = 0.32 and U = $1.1 \text{ W/m}^2\text{K}$) when installed externally
- Waterproof, weather-resistant and UV fading resistant
- Health/Safety: conforms to standard requirements for buildings open to the


TECHNICAL DATA

SATINÉ 21154							
Composition	28% Fibreglass - 72% PVC						
Fire, smoke classification and other official test reports	M1 (F) - NFP 92 503 BS (GB) - 476 Pt 6 & 7 Class 0 C UNO (IT) - UNI 9177		Euroclass C-s3-d0 (EU) - EN 13501-1 mounted according to EN 13823 & EN 14716 HHV: 14,2 MJ/kg (9,40 MJ/m²)				
Openness factor	0%						
Opacity	100% at 100.000 lux						
UV screen	100%						
Width	210 cm						
Weight/m²	660 g ± 10% - ISO 2286 - 2						
Thickness	0,75 mm ± 10% - ISO 2286 - 3						
Colour Fasteness to light (scale of 8)	Screen side: 7 - ISO 105 B02 (white not graded) Backing side: 7/8 ISO 105 B02 and ISO 105 B04						
Mechanical resistance	Breaking	Tear		Folding			
Warp	> 225 daN/5 cm	≥7 daN		≥ 150 daN/5 cm			
Weft	> 190 daN/5 cm	≥7 daN		≥ 100 daN/5 cm			
	ISO 1421	EN 1875-3		ISO 1421**			
Elongation (warp and weft)	< 5% - ISO 1421						
Packaging	Rolls of 33 lm						
Making up	Advice note on request - Making up of fabric panels with retentive systems on the side edges (with retentive buttons/studs, deep side channels)						

This product's technical data are in conformity with this brochure as of the date of publication. MERMET SAS reserves the right to change the technical data; only those provided on the company's website www.sunscreen-mermet.com shall be deemed to be authentic. Where applicable, MERMET SAS also reserves the right to withdraw this product from sale should any of the technical properties or characteristics set out above prove to be inadequate or rendered impossible as a result of a change in regulations or in knowledge or understanding.


* Reports available on request, please contact Mermet

** Internal procedure derived from ISO 1421 standard



SERVICE •

- Calculation of solar factor gtot (glazing + blind)
- Spectral values and thermal & optical factors available on request
- Specification sheet
- A4 samples and prototypes
- Training on fabrics functionality



THERMAL AND OPTICAL FACTORS in the European standard EN 14501


SATINÉ 21154	Thermal factors					Optical factors
OF 0%	Fabric		Fabric + Glazing / gtot external blind			
Colours	Ts	Rs	As	C : gv = 0,59	D : gv = 0,32	Tv
Grey Backing	0	34	66	0,02 4	0,02 4	0
0202 White	0	69	31	0,01 4	0,01 4	0
2020 Linen	0	55	45	0,02 4	0,02 4	0
0210 White Sable	0	53	47	0,02 4	0,02 4	0
0707 Pearl	0	39	61	0,02 4	0,02 4	0
0102 Grey White	0	42	58	0,02 4	0,02 4	0
0101 Grey	0	21	79	0,03 4	0,02 4	0
3030 Charcoal	0	6	94	0,03 4	0,03 4	0

gv = 0.59: Solar factor of standard glazing (C), low-emission 4/16/4 double glazing filled with Argon (U value thermal transmittance = $1.2 \text{ W/m}^2\text{K}$). gv = 0.32: Solar factor of standard glazing (D), reflecting low-emission 4/16/4 double glazing filled with Argon (U value thermal transmittance = $1.1 \text{ W/m}^2\text{K}$).

Comfort classification according to EN 14501 standard: 0 very little effect 1 little effect 2 moderate effect 3 good effect 4 very good effect

Samples tested according to EN 14500 standard defining the measurements and calculation methods as specified in the standard EN 13363-2 "Solar protection devices combined with glazing calculation of solar and light transmittance - part 2: EN 13363-2 detailed method" and EN 410 "Glass in building - Determination of luminous and solar characteristics of glazing".




















MERMET COLLECTION offers **a wide choice of fabrics** for external and internal application, from transparency to total darkness, for thermal and optical comfort.

To receive other brochures from the collection, **contact us.**



SCREEN VISION / DESIGN / THERMIC / LOW E

EXTERNAL SCREEN CLASSIC

SCREEN NATUR

BLACKOUT 100 %

ACOUSTICS



58, chemin du Mont Maurin - 38630 Les Avenières Veyrins-Thuellin - France Tel. +33(0) 474 336 615 - Fax +33(0) 474 339 729

Mermet

A division of the brand

This brochure must be read and interpreted in accordance with the General Terms & Conditions of Sale of MERMET SAS, with which it forms an indissoluble whole. The General Terms & Conditions of Sale that are current at any time are those contained on the MERMET SAS website at the following address: www.sunscreen-mermet.com.